
P.O. Box 190 - 1 Logan Street Truro, Nova Scotia Canada B2N 5C2 902-895-5406 Fax: 902-893-8187 e-mail: inquiries@stanfields.com



Specification KL23



NFPA 1971-2007 Edition



9723ES

Measurements 9723ES	
A-B	4.0"
C-D	8.5"
E-F	6.5"
H-I	10.5"
G-J	4.0"
J-L	6.0"
H-N	8.0"
A-K	13.0"
K-M	3.0"

Part Number: KL23

Fabric:

Content: 49/49/2 Kermel/LenzingFR/Spandex

Weight: 8.4 oz sq yd Construction: 1x1 Rib Knit

Stretch: 100% Color: Navy Blue

Head Desian:

Style: Separate head with sewn on back and front bib. The back of the head ends at the nape of the upper neck. The back bib is sewn at this point.

Lavers: Two

Measurements: See chart above

Bib Design:

Style: A two piece double layer yoke style bib is sewn to the head and forms a neck seam. The front and back bib are joined at the shoulder to form a notched shoulder seam on either side of the head.

Layers: Two

Measurements: See chart above

Face Openina:

Face Opening Sewn with ½ inch elastic Relaxed Measurement: 5 to 5.5 inches

Fully Stretched Measurement: Exceeds 15 inches

Construction:

Head Seams: All head and bib seams sewn with flat lock stitch.

Face Opening: Elastic sewn to edge with three thread overlock stitch; turned under and sewn

with a two needle cover stitch.

Binding: One and a half inch binding sewn to hem through folder with a three thread cover stitch to create a $\frac{1}{2}$ inch finished bound hem.

Thread: 100% Nomex

Labels:

FR label. All four label edges sewn to the hood.

Certification:

Classified by Underwriters Laboratories to meet NFPA Standard 1971 2007 edition.

Test Results

NFPA ASTM: Electric Arc

Thermal Protective Performance TPP Arc Thermal Performance Value APTV: 38 cal/cm²

Before Washing: 31.6
After Washing: 40.8

Heat Attenuation Factor HAF: 93%

Flame Resistance Test One

After Flame Before Washing: 0 sec After Flame After Washing: 0 sec Char Length Before Washing: 38 mm

Char Length After Washing: 29 mm