


## Description

Reflexite® German Police Film+ is a tough weather resistant product designed for rugged outdoor use. The material is die cuttable and plotter cuttable, and easy to apply onto smooth painted or unpainted vehicle surfaces. The material does not need edge sealing.

## Product Construction

Reflexite® German Police Film+ is composed of cube corner (microprism) retroreflective elements integrally bonded to a flexible, smooth-surfaced tough and weather resistant UV stabilized polymeric film. The prism surfaces are coated with a vacuum deposition of aluminium to provide a mirror surface to the prism facets. The resulting material is not more than 0,20 mm thick, and comes with an aggressive high-tack pressure sensitive adhesive. The product is single layer, with no need for edge sealing.

## Film Logo Pattern



## Colour

Reflexite® German Police Film+ is available in white. The colour shall be located in the area defined by the chromaticity coordinates and luminance factor provided in Table 2, when measured in accordance with the provisions of CIE No.15.2. The four pairs of coordinates determine the acceptable colour when measured with standard illuminant D<sub>65</sub> using a Hunter LabScan.

The retroreflected colour (nighttime colour), when illuminated with CIE standard illuminant A at an observation angle of 20' and entrance angles of  $\beta_1 = \pm 5^\circ$ , and  $\beta_2 = 0^\circ$  shall be located within the area defined by the chromaticity coordinates in Table 3.

## Retroreflectivity

When illuminated with CIE standard illuminant A and measured with the provisions of CIE No. 54, the coefficient of retroreflection for Reflexite® German Police Film+ shall be not measure less than the values in Table 1 when rotation angles of 0° and 90° are measured and averaged.

## Impact Resistance

Reflexite® German Police Film+ sheeting shall show no signs of cracking or delamination outside the actual area of impact when it is subjected to an impact of 1,13 N·m generated by a 0,91 kg weight with a 16 mm rounded tip, as per ASTM D4956.

## Adhesive

The adhesive is protected by a release liner, which shall be removed by peeling, without soaking in water or other solvents. A 25 mm strip shall provide a bond such that it shall support a 800 g weight for 5 minutes without the strip peeling for a distance of more than 50 mm when applied to a smooth aluminium surface as specified in the ASTM 4956 adhesion test. Reflexite® German Police Film+ may be used on stainless steel when used with the correct pressure sensitive adhesive, which should be requested when ordering.

## Shrinkage

A 230 mm square specimen of the sheeting with liner shall be conditioned a minimum of 1 hour at 22° C and 50% RH. The liner is then removed and the specimen is placed on a flat surface with the adhesive side up. 10 minutes after the liner is removed and again after 24 hours, then specimen is measured to determine the amount of dimensional change. The specimen must not shrink in any dimension more than 0,8 mm in 10 minutes and 3,1 mm in 24 hours.

**Flexibility**

The sheeting is conditioned for 24 hours at 22° C and 50% RH. The release liner is removed and the sheeting must be sufficiently flexible to show no cracking when bent in one second's time around a 3,1 mm diameter mandrel with the adhesive contacting the mandrel.

**Application Instructions**

Material must be applied when the film and substrate temperature is between 15° C and 38° C to assure proper adhesive bonding. Surfaces must be cleaned for II grease, oil and dirt. Use a clean towel and Isopropyl alcohol or similar to wipe the surface before application. If any air bubbles are trapped, use a pin to puncture the bubble and squeegee to push the air towards the pin hole.

Please contact ORAFOL for complete application instructions.

**Shelf Life**

The sheeting must be used within 1 year from the shipment date. All rolls including partially used rolls should be stored in original packaging, tightly wound. Store in a clean and dry area, away from direct sunlight. Store at 20° C and 50% relative humidity.

**Table 1 - Retroreflectivity**

Observation Angle	Entrance Angle ( $\beta_2, \beta_1=0$ )			
	5°	30°	40°	60°
0.33°				
White	450	200	90	16

All values have units of cd/lux/m<sup>2</sup>.

**Table 2 - Colour Specification Limits (Daytime)**

Colour	Chromaticity Coordinates*								
	1		2		3		4		Y
	x	y	x	y	x	y	x	y	
White	0,300	0,270	0,385	0,355	0,345	0,395	0,260	0,310	≥ 0,25

\*) The four pairs of chromaticity coordinates determine the acceptable chromaticity when measured with standard illuminant D65 using a Hunter LabScan.

**Table 3 - Colour Specification Limits (Nighttime)**

Colour	Chromaticity Coordinates*							
	1		2		3		4	
	x	y	x	y	x	y	x	y
White	0,373	0,402	0,417	0,359	0,450	0,513	0,548	0,414

\*) The four pairs of chromaticity coordinates determine the acceptable chromaticity when illuminated with CIE standard illuminant A at an observation angle of 20' and entrance angles of  $\beta_1=+/- 5^\circ$ , and  $\beta_2=0$ .

**IMPORTANT NOTICE**

All Reflexite® and ORALITE® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning Reflexite® and ORALITE® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of Reflexite® and ORALITE® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice. Reflexite® is a registered trademark of ORAFOL Europe GmbH.